Starting Point Formulation



High Solid, High Gloss Decorative Coating

with Borchi® OXY-Coat High-Performance Catalyst

New MEKO Regulation in the EU effective March 1st, 2022

GHS labeling will require 1B carcinogen with concentration limit at $\ge 0.1\%$.

Improved Dry Times

Even Under Adverse Conditions

and After Storage

30

25

20

15

10

5

0

Control


Standard Conditions

Loss of Dry (14 Days 50°C)

Dry Time in Hours

Improved Gloss

Initially and After 330 Hours Q-Fog and Accelerated Weathering Test



Borchi® OXY-Coat Formulation:

- Low VOC
- Cobalt-Free
- Oxime-Free
- More Durable

High Glos	s Decorative	Coating
-----------	--------------	---------

Material	Control	Borchi [®] OXY-Coat
Synolac [®] 4060 WP 90	14.90	14.90
Octa-Soligen [®] Calcium 10, basic	0.93	0.93
Exxol D60	5.00	5.00
Borchi [®] Gen 1252	0.07	0.07
Tioxide TR 92	34.78	34.78
Synolac [®] 4060 WP 90	36.67	36.67
Exxol D60	7.65	7.65
TOTAL	100.00	100.00
6% Cobalt / 9% Zr Combination Drier	0.46	0.00
Borchi® OXY-Coat - Cobalt-free	0.00	0.45
МЕКО	0.31	0.00
Borchi [®] Shield - MEKO-free	0.00	1.00
TOTAL	100.77	101.45

Adverse Conditions (10°C, 80% Humidity)
Better Anti-Skinning Performance

After 2 Weeks at 50°C in the Oven

Borchi® OXY-Coat



Less Yellowing After 2 Weeks at 50°C in the Oven



Higher Corrosion Resistance Q-FOG Salt Spray After 330 h



For more information, please reach us at **borchers.com/contact**

PLEASE NOTE: As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warrantly and without accepting any responsibility/liability. Each customer must test and be responsible for its own specific use, further processing, labeling, marketing, etc. All sales are exclusively subject to our standard terms of sale posted at www.fmillken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing. Borchi is a trademark of Borchers Americas.

Milliken

SYNO4060WP-02.03.2025